

a3

1. **(Once Amended)** A method of depositing a wiring thin film on a semiconductor substrate, comprising the steps of:

depositing a Ti film; and

depositing Al-Si-Cu film on the Ti film at a temperature of at least 400 °C to form a layer of Al₃Ti, which prevents Si-recrystallization in a subsequent cooling process.

13

2. **(Once Amended)** A method of depositing a wiring thin film on a semiconductor substrate, comprising the steps of:

depositing a Ti film; and

depositing Al-Si-Cu film on the Ti film; and

annealing the semiconductor substrate at a temperature of at least 400 °C to form a layer of Al₃Ti, which prevents Si-recrystallization in a subsequent cooling process.

(2). Please add the following claims:

a4

8. **(Newly Added)** A method as recited in claim 1, further comprising, after said forming said layer of AlTi₃, patterning an Al layer.

13

9. **(Newly Added)** A method as recited in claim 2, after said forming said layer of AlTi₃, patterning an Al layer.